

Category > Protect

X-Link™ E (WL)

Modified Urethane in Wet Look Finish

Product Description

Ameripolish® X-Link E (WL) is a modified urethane high-gloss sealer. Modified from our original X-Link WL, X-Link E (WL) provides a true wet look. X-Link E (WL) is extremely durable and breathable from beneath the concrete. X-Link E (WL) is designed for use with ColorJuice Extreme, but can be used to seal natural concrete as well as other cementitious surfaces such as porous brick, natural and manufactured stone, stucco, slate, and flagstone.

Features

- RTU = Ready to use
- “Wet-Look” finish
- Non-yellowing finishes
- Breathable and fast-drying
- Oil and chemical resistant
- Added mildew and UV protection
- For outdoor applications
- Penetrating and durable
- Fast application, 1 hour drying
- Water-based
- Can be applied to most cementitious surfaces, other unglazed stone, and masonry surfaces

Uses

- Ameripolish® X-Link™ E (WL) exterior masonry and concrete-type surfaces.
- Use on colored or uncolored, stamped or exposed aggregate concrete, porous brick, natural and manufactured stone, stucco, slate, unglazed tile and flagstone.

Dilution & Coverage

Ameripolish® X-Link™ E (WL) is shipped Ready to Use (RTU) and should not be mixed with any other chemical. Approximate coverage rate is 500-1000 sqft per gallon depending on the porosity of concrete or other surfaces.

Product Specification

Application:	Spray on
Appearance:	Milky
VOC:	Compliant (5g/l)
Shelf life:	1 year
Solvent:	Water-Based

Packaging Specification

Product #	Shipping Wt.	Container
XS-1	10 lbs.	1 gallon RTU
XS-5	50 lbs.	5 gallons RTU
XS-30	300 lbs.	30 gallons RTU
XS-55	550 lbs.	55 gallons RTU
XS-250	2,500 lbs.	250 gallons RTU



Category > Protect

X-Link™ E (WL)

Modified Urethane in Wet Look Finish

Preparation

WARNING: People, property, vehicles, animals, plants, and all surfaces not intended to be sealed should be protected from the product, splash, over-spray, and wind drift, using polyethylene sheeting or other proven protective material. **NEW CONCRETE MUST CURE FOR AT LEAST 28 DAYS BEFORE APPLICATION.** For best results, perform a moisture content test on both newly-poured and existing slabs. Slabs with a moisture content 5 lbs per 1000 sf or less show best performance (ASTM F1869 calcium chloride test). High moisture levels may affect performance of sealer. Do not apply if concrete is frozen, dirty or has standing water. Hydrostatic pressure may affect sealer performance. Surface to be sealed must be completely clean. Remove efflorescence, oil, dirt, wax, paints, sealers, and curing compounds; pressure wash and/or power scrub if necessary. Ameripolish® Strip & Clean™ is highly recommended to clean the surface.

Application

1. Prior to starting project, apply X-Link™ E (WL) to sample area of each type of concrete to be treated, using application procedures proposed for project. Confirm that concrete is receptive to sealer.
2. Ambient temperature during application should be 55°F-80°F (12.8°C-26.7°C). Do not apply on rainy, foggy, or extremely humid days. Excess moisture may prevent sealer from drying properly.
3. Apply X-Link™ E (WL) using an Ameripolish® Sprayer fitted with a conical mist tip gray #8.
4. Spray X-Link™ E (WL) with the conical tip sprayer in circular motions approximately 18 inches from the project surface.
5. Apply 2 applications for optimal performance and true wet look sheen.

Foot traffic may be allowed on sealed surface after 2-4 hours. For heavy traffic, allow 24 hours curing.

Sealed surface should be inspected periodically for areas of thin or traffic worn sealer, and sealer reapplied as needed. Normal traffic may require reapplication of X-Link™ E (WL) annually. Use Ameripolish® Rejuvenating Cleaner

Concentrate® for long lasting protection.

Cleanup

Remove dust and debris with broom, vacuum, water hose, mop or auto-scrubber. Ameripolish® X-Link™ E (WL) should be reapplied every 2-3 years, or more often if deemed necessary.

Storage

- Store upright in safe dry place at 40-110F° (4 -43C°)
- Keep product from freezing
- Keep out of reach of children
- Seal container after use
- Do not mix with other chemicals

VOC Compliance

In addition, Ameripolish® X-Link E (WL) offers VOC compliance with low VOC at 5g/L and is also compliant with national, state and district regulations:

- US Environmental Protection Agency
- California Air Resources Board SCM Districts*
- South Coast Air Quality Management District*
- Maricopa County, AZ
- Northeast Ozone Transport Commission*

*Before application, verify product conformance with local and state codes.

Warning & Safety Information

KEEP OUT OF REACH OF CHILDREN. DO NOT TAKE INTERNALLY. BEFORE USING THIS PRODUCT PLEASE READ THE SAFETY DATA SHEET IN ITS ENTIRETY! Safety Data Sheets (SDS) can be found online at www.ameripolish.com or upon request by contacting Ameripolish at 1-800-592-9320.

Warranty

The information contained herein is believed to be reliable. This information is based on laboratory testing and results. Because of variations in methods, conditions and equipment, each user must test this product to make

Category > Protect

X-Link™ E (WL)

Modified Urethane in Wet Look Finish

a judgment of performance. Applicator is responsible for testing material for effectiveness and performance. Manufacturer obligation is limited to the refund of purchase price or replacement of material if proven to be defective. Claims must be made in writing and received within one year from date of product sale to original buyer. Sole remedy shall be replacement of product proven defective.